



Ref.	Description	Tolerances		Resistance to Flexibility		Abrasion (Wear and Tear)	Water Absorption
		Flatness & Curvature	Thickness	T (Mpa)	P(kN)	(cm ³ /cm ²)	(%)
3.0201.xx	Distintus 400x600x20	=± 0.3 %	=± 2mm	8.67	2.33	10.10	6.90
	Distintus 400x600x30			6.27	5.63		
	Distintus 600x600x25			8.40	3.50		
	Distintus 600x600x30			6.10	5.50		
2.0203.xx	Estilhados 380x580x20			7.75	2.05	8.50	6.00
	Estilhados 380x580x30			5.45	4.77		
	Estilhados 580x580x25			8.19	3.74		
	Estilhados 580x580x30			5.93	5.80		
2.0303.xx	Imensus 400x600x20			8.50	2.23	13.40	7.40
	Imensus 400x600x30			5.95	5.26		
3.0302.xx	Tiburtinus 400x600x20	8.97	2.40	13.48	6.60		
	Tiburtinus 400x600x30	6.28	5.66				
3.0101.xx	Empedrado Esp. 2cm	7.92	3.48	10.12	6.66		

Updated on 05 – 04 – 2006

Checked by:
Eng.^o Mario Dinis
Dir. of Quality (Proc. By Computer)

The values above are the results of the test conducted in proper laboratory conditions in accordance with standard **EN13748-2:2004 Terrazzo tiles. Terrazzo tiles for external use** on the various materials listed above.